

Typical Properties of HyPUR-cel® T0812

Polymer	Polyurethane			
Physical Property	Test Method	Units	Typical	Tolerance
Density	ASTM D3574	pcf	8	6.5 – 9.5
Compression Deflection 25%	ASTM D1056	psi	12	9 - 15
Compression Set 50%	ASTM D1056	%	1.7	3 max
25% CFD	ASTM D3574	psi	7.5	N/A
Tensile Strength	ASTM D3574	psi	90	N/A
Elongation	ASTM D3574	%	60	N/A
Tear Strength	ASTM D624	lb./in	6.5	N/A
Resilience	ASTM D2632	%	41	N/A
Flammability	FMVSS-302	In/min	Pass @ .079” or Thicker	
Service Temperature	N/A	F	-40 to 250	

Product Availability

- Standard 60 inch (1.52 meter) wide rolls with capabilities to produce in various widths.
- Available in 50 feet (15.24 meters) and 100 feet (30.48 meters) lengths, skived to custom thicknesses.
- Available with adhesives, laminated fabrics, films, custom coatings or composites.
- Various color options available with the ability to custom color match using our fully reacted colorants.
- Other additives, such as anti-microbial and flame retardants, are available depending upon volume.

Characteristics

- Breathable
- Thermoformable
- Low Compression Set
- Dimensionally Stable

Disclaimer: This information is furnished as a guide for selecting materials. Rubberlite Inc. makes no warranties, expressed or implied, of merchantability with respect to the goods or that such goods are fit for any particular purpose. It is the customer's responsibility to obtain and test samples when determining suitability of material for a particular application.

