

## Typical Properties of HyPUR-cel® V12200

Polymer	Polyurethane			
Physical Property	Test Method	Units	Typical	Tolerance
Density	ASTM D3574	pcf	12	10 - 14
CFD 25%	ASTM D3574	psi	3.5	2 - 6
Compression Set 50%	ASTM D1056	%	0.1	3 max
Compression Set 50%	ASTM D3574	%	0.6	5 Max
Tensile Strength	ASTM D3574	psi	70	N/A
Elongation	ASTM D3574	%	190	N/A
Tear Strength	ASTM D624	lb./in	11	N/A
Resilience	ASTM D2632	%	5	N/A
Service Temperature	N/A	F	-40 to 250	

### Product Availability

- Standard 60 inch (1.52 meter) wide rolls with capabilities to produce in various widths.
- Available in 50 feet (15.24 meters)' and 100 feet (30.48 meters) lengths, skived to custom thicknesses.
- Available with adhesives, laminated fabrics, films, custom coatings or composites.
- Various color options available with the ability to custom color match using our fully reacted colorants.
- Other additives, such as anti-microbial and flame retardants, are available depending upon volume.

### Characteristics

- Breathable
- Thermoformable
- Low Compression Set
- High Stretch
- Dimensionally Stable
- Impact Resistance

*Disclaimer: This information is furnished as a guide for selecting materials. Rubberlite Inc. makes no warranties, expressed or implied, of merchantability with respect to the goods or that such goods are fit for any particular purpose. It is the customer's responsibility to obtain and test samples when determining suitability of material for a particular application.*

